

ARCADE FR



UPF 50+



500 g/m²



M2 / B1 / BS
NFPA701
B-s2-d0



1.50 m
3.02 m



Gama
kolorów



DICKSON
COATINGS

ARCADE FR

Nośnik <i>Support / Trägergewebe / Soporte / Supporto</i>	550dtex PES HT
Szerokość <i>Laize / Breite / Ancho / Altezza</i>	1.50 - 3.02 m
Powłoka <i>Enduction / Beschichtung / Revestimiento / Spalmatura</i>	PVC (Lowick)
Wykończenie <i>Finition / Ausrüstung / Acabado / Finizione</i>	Cleangard
Waga całkowita <i>Poids Total / Gesamtgewicht / Peso total / Peso totale</i>	500 g/m ²
Wytrzymałość na zerwanie > NF EN ISO 1421 <i>Résistance rupture / Reissfestigkeit Resistenci a la rotura / Resistanza alla rottura</i>	150/150 daN
Wytrzymałość na rozdarcie > DIN 53363 <i>Resistance déchirure / Weiterreissfestigkeit Resistencia al desgarro / Resistenza allo strappo</i>	15/15 daN
Przyczepność > NF EN ISO 2411 <i>Adherence / Haftung / Adherencia / Aderenza</i>	7 daN / 5 cm
Wydłużenie pod naciskiem (Osnowa / Wątek) > NF EN 15619 <i>Allongement sous charge (Ch / Tr) Verbleibende Verformung (K / S) Alargamiento bajo carga (urdimbre / trama) Allungamento sotto loricato (ordito / trama)</i>	<1% / <3%
Deformacja cząstkowa (Osnowa/ Wątek) > NF EN 15619 <i>Déformation résiduelle (Ch / Tr) / Dehnung unter Last (K / S) Deformación residual (urdimbre / trama) Deformazione re*idua (ordito / trama)</i>	<0.4% / <1.2%
Wytrzymałość na temperaturę > NF EN 1876-2 <i>Températures d'utilisation / Temperaturbeständigkeit Resistencia máxima a la temperatura / Resistenza alla temperatura</i>	-30°C +70°C
Trudno zapalność > NF P 92503 / DIN 4102 / BS 7837 <i>Ignifugation / Brennverhalten / Ignifugación / Ignifugazione</i>	M2 / B1 / BS NFPA701 B-S2-D0

Wartości średnie pozaumowne
Valeurs moyennes, non-contractuelles / Alle angegebenen Werte sind ca. Werte Valores medios y no contractuales / Questi valori medi non hanno valore contrattuale

REF.	RAL	M	MB
867	9010	1,50-3,02	30-60
7462		1,50-3,02	30-60
7458	1015	1,50-3,02	30-60
654		1,50-3,02	30-60
7379	7040	1,50-3,02	30-60
7534		1,50-3,02	30-60
7426		1,50-3,02	30-60
7419		1,50-3,02	30-60
810	9005	1,50-3,02	30-60
7450	5015	1,50-3,02	30-60
941		1,50-3,02	30-60
7309	50*3	1,50-3,02	30-60
995	6026	1,50-3,02	30-60
7533		1,50-3,02	30-60
7456	1003	1,50-3,02	30-60
7507	3002	1,50-3,02	30-60

SYSTEM
LOWICK

MADE IN
FRANCE



FINITION
CLEANGARD

REACH
COMPLIANCE



DICKSON COATINGS

415, avenue de Savoie
Saint Clair de la Tour
F-38357 La Tour du Pin
Tel (+33) 04 74 83 51 00
Fax (+33) 04 74 83 51 01

www.dickson-coatings.com



GLEN RAVEN™

Glen Raven jest marką a Dickson® jest zarejestrowaną marką handlową Glen Raven, Inc