

TEXTURA



360 g/m²



3.20 m



M2 - BS

TEXTURA



360 g/m²



3.20 m



M2 - BS

Nośnik

Support / Trägergewebe / Soporte / Supporto

2*167 / 550 dtex
PES HT

Szerokość

Laize / Breite / Ancho / Altezza

3.20 m

Długość

Longueur / Rollenlänge / Largo / Lunghezza

30 - 60 mb

Grubość

Epaisseur / Dicke / Espesor / Spessore

0.33 mm

Powłoka

Enduction / Beschichtung / Revestimiento / Spalmatura

PVC
(Lowick)

Wykończenie

Finition / Ausrüstung / Acabado / Finizione

Cleangard

Waga całkowita

Poids Total / Gesamtgewicht / Peso total / Peso totale

360 g/m²

Odporność na rozerwanie > NFEN ISO

*1421 Résistance rupture / Reissfestigkeit
Resistencia a la rotura / Resistenza alla rottura*

150 / 190
daN / 5cm

Odporność na rozdarcie > DIN 53363

*Résistance déchirure / Weiterreissfestigkeit
Resistencia al desgarro / Resistenza allo strappo*

14 / 22 daN

Przyczepność > NF EN ISO 2411

Adhérence / Haftung / Adherencia / Aderenza

5 daN / 5 cm

Odporność na temperaturę > NF EN

*1876-2 Températures d'utilisation /
Temperaturbeständigkeit /
Resistencia máxima a la temperatura /
Resistenza alla temperatura*

-30°C
+70°C (24h)

Trudno zapalność


> NF P 92503 / BS 7837

*Ignifugation / Brennverhalten / Ignifugación /
Ignifugazione*

M2 / BS
(NFPA - B1 -
EUROCLASS:
w trakcie)



654



7462









7311

*Wartości średnie, pozaumowne /
Valeurs moyennes, non-contractuelles /
Alle angegebenen Werte sind ca. Werte
Valores medios y no contractuales /
Questi valori medi non hanno valore
contrattuale*

TEXTURA



			Gtot EXT	
 654	47	49	0.08	3
 7462	68	15	0.13	15
 7311	68	13	0.14	18



Odbicie ciepła (%)

*Réflexion Solaire (%) / Wärme Reflektion (%)
Reflexión Solar (%) / Riflessione Solare (%)*



Pochłanianie ciepła (%)

*Absorption Solaire (%) / Wärme Absorption (%)
Absorción Solar (%) / Assorbimento Solare (%)*



Gtot EXT Współczynnik solarny kombinacji tkaniny + referencji szklenia C

*Facteur solaire de l'ensemble toile + vitrage de référence C
Gesamtenergiedurchlassgrad der Kombination Verglasung C + Sonnenschutz
Factor solar de la combinación del tejido + vidrio de referencia C
Fattore solare dell'insieme telo + vetro di riferimento C*



Transmisja światła (%)

*Transmission Visuelle (%) / Licht Transmission (%)
Transmisión Visual (%) / Transmissione Visiva (%)*

SYSTEM
LOWICK

FINITION
CLEANGARD

MADE IN
FRANCE

vinyl plus
COMMITTED TO
SUSTAINABLE DEVELOPMENT

REACH
COMPLIANCE


DICKSON[®]
COATINGS

DICKSON COATINGS

415, avenue de Savoie
F-38110 Saint-Clair-de-la-Tour

Tel. (+33) 04 74 83 51 00
Fax (+33) 04 74 83 51 01

www.dickson-coatings.com



GLEN RAVEN™

Glen Raven™ jest marką handlową a Dickson® zastrzeżonym znakiem towarowym of Glen Raven, Inc.

07/2019